

180 Degree (Kanvas)

Technical Specification

Construction

Tufted multi-height loop pile

Face Yarn

100% Nylon 6,6 BCF

Total Pile Mass

712g/m² (21 oz/yard²)

Dye Method

Dye Injection / SDN

Gauge

40 per 10cm (1/10th gauge)

Rows

36.3mm average

Finished Pile Height

3.1mm average

Total Thickness

6.7mm average

Backing

Polymer matrix with fibreglass reinforced Inertial Backing System (IBS)

Module Size

457.2mm X 457.2mm

Box Quantity

5.016m² (24 tiles per box)

Total Weight

4,612g/m²

Performance Specification



Flammability

Radiant Panel Test ISO9239-1
 - CRF > 2.8kW/m²
 - Smoke < 749%. minutes



Dimensional Stability

International Aachner Test:
 - Less than 0.2% at both primary and secondary backing levels



Electrostatic Propensity

Less than 3.5kv at 21°C and 20% RH



Bulk Resistance

5 x 10⁵ to 2 x 10¹⁰ OHMS



Edge Integrity

No unravelling at edge of module



Colourfastness

Meets or exceeds the relevant Australian standard in the following tests:
 - To light Xenon Arc Test: (5-6)
 - To shampoo AS2111.19.2 (3-4)
 - To rubbing AS 2111.19.1 (4) (wet & dry)



Soil Protection

Soil and stain protection applied



Castor Chair Test

BS.EN985 Pass

Applicable Warranties



**15 year
Wear Warranty**



**15 year
Dimensional Stability warranty**



**15 year
Anti-Static Warranty**



**15 year
Castor Chair Wear Warranty**



Lifetime Design Availability

Environmental Assessment



ACCS-ECS Level 4

(Certificate No. 11118)



Maximum available credit points in the following sections of Green Star:

- Materials (Flooring Calculator)
- IEQ (Low VOC Emissions)
- PVC Credit available upon request



EarthPlus® Program

Product take back program



Environmental Stewardship

High post-consumer recycled content

ACCS Grading

CEHD&S – Commercial Extra Heavy Duty and stairs (Certificate No. 11118)

Installation

Grid Stick method using low-VOC water based acrylic adhesive as per AS 2455 Parts 1 & 2

General

Specifications are subject to normal manufacturing tolerances and may be altered without notice. Production may vary from dye-lot to dye-lot

